

JACOBS & THOMPSON INC.

TECHNICAL DATA

FOAMFLEX # 1357

Property	Specification	Test Method
Composition	PVC	
Cell Structure	Closed	
Density (pcf)	7.0	ASTM D 1667
50% CFD (psi)	0.72 – 2.0	GM6086M TYPE 1A
Tensile Strength (psi)	25 min.	ASTM D 412
Elongation (%)	100 min.	ASTM D 412
Water Absorption (volume, %)	10 max.	GTP ¹
Recommended service temp. (°F)	-40 to 180	
Recommended application temp. (°F)	50 to 110	
Fungi Resistance	Excellent	
Oxidation Resistance	Excellent	
Weather Resistance	Excellent	
Adhesion	Pass	GM3607M

REV. 003

REV. DATE: 03/10/00

Jacobs & Thompson cannot anticipate all conditions under which this information and our products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. Unless otherwise agreed in writing, we sell the products without warranty and users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purpose.