



TECHNICAL BULLETIN

Haltech Inc.



465 CORONATION DRIVE
SCARBOROUGH, ONTARIO M1E 2K2
TELEPHONE: (416) 284-6111
FAX: (416) 284-6932

HALLMARK 848 LV

BASE:	SBR
TOTAL SOLIDS %:	33.0 – 37.0
VISCOSITY CPS @ 24°C:	600 - 800
RELATIVE DENSITY:	0.79 - 0.81
SOLVENT:	FLAMMABLE
COLOUR OF DRIED FILM:	NATURAL
CLEANER:	HALLMARK 78 , NAPHTHA, VARSOL
APPLICATION METHOD:	SPRAY, BRUSH, ROLLER
SHELF LIFE:	6 MONTHS

HALLMARK 848 LV IS USED FOR BONDING INSULATION MATERIALS TO METAL, WOOD, MASONRY AND PLASTICS IN A ONE WAY WET STICK OR TWO WAY DRY STICK PROCEDURE. THE OPEN TIME IN A ONE WAY BONDING IS ABOUT 10 - 15 MINUTES, DEPENDING UPON COATING WEIGHT. **HALLMARK 848 LV** HAS AN EXCELLENT SPRAY PATTERN AND THUS WILL PROVIDE MILEAGE OF UP TO 600 SQ. FT./GALLON.

CAUTION:

THIS PRODUCT CONTAINS VOLATILE FLAMMABLE SOLVENT. PROVIDE ADEQUATE VENTILATION. AVOID SPARKS. DO NOT USE NEAR OPEN FLAME, OR SPARK PRODUCING EQUIPMENT.

WARRANTIES:

There is NO WARRANTY or condition, OF ANY KIND, written or oral, express or implied (INCLUDING NO WARRANTY OR MERCHANTABILITY OR FITNESS OF THE GOODS FOR THE PURPOSE CONTEMPLATED BY BUYER) concerning the goods sold hereunder or containers in which shipped and none shall be implied by law, EXCEPT THAT THE GOODS SHALL BE IN ACCORDANCE WITH SELLER'S SPECIFICATIONS.